

Abstract of the Disclosure

A lithium secondary battery includes an electrode body obtained by winding or laminating a positive electrode and a negative electrode via a separator, and a non-aqueous

- 5 electrolytic solution containing a lithium compound as the electrolyte. The non-aqueous electrolytic solution contains water (H_2O) and hydrofluoric acid (HF) in a total concentration of 10,000 ppm or less. Owing to the restriction of the total concentration of water and
- 10 hydrofluoric acid contained in the non-aqueous electrolytic solution, the lithium secondary battery can suppress the deterioration of battery properties caused by the water and hydrofluoric acid and has excellent cycle property and reliability.